



16

HARMONIZE STANDARD : <b>TS EN 1469</b>
PRODUCTS : <b>NATURAL STONE PRODUCTS FOR CLADDING</b>
PETROGRAPHIC DESCRIPTION : <b>TRAVERTINE</b>
PLACE OF USE : <b>INDOOR - OUTDOOR</b>
PRODUCT NAME : <b>RED TRAVERTINE</b>

COMPANY  
NAME /  
ADDRESS

LUXMAR MADENCİLİK SANAYİ VE TİCARET LİMİTED ŞİRKETİ  
Hızırbey mahallesi 111.cadde No: 109/111  
Merkez, Isparta / TURKEY

Web : [www.luxmarstone.com](http://www.luxmarstone.com)

E-mail : [info@luxmarstone.com](mailto:info@luxmarstone.com)

CHARACTERISTICS	DECLARATION	TEST METHOD
FIRE RESISTANCE	CLASS A1	WITHOUT TEST (96/603/EC)
FLEXURAL STRENGTH Mpa	10,07	TS EN 13161
FROST RESISTANCE Mpa	78	TS EN 12371
APPARENT DENSITY kg/m <sup>3</sup>	2400	TS EN 1936
OPEN POROSITY %	3,09	TS EN 1936
ABRASION STRENGTH mm	NPD	TS EN 14157
WATER ABSORPTION BY CAPILLARY OF WEIGHT g/m <sup>2</sup> .s <sup>0,5</sup>	1,86	TS EN 1925
WATER ABSORPTION AT ATMOSPHERIC PRESSURE BY WEIGHT	1,4	TS EN 13755